

**IN THE CLAIMS:**

**Please cancel** claims 1-10. **Please also amend** claims 11-15 as shown in the complete list of claims that is presented below.

Claims 1-10 (cancelled).

11. (original) The semiconductor device fabricating method of claim 10, 13, wherein the fluorocarbon gas includes at least one selected from the group consisting of C<sub>4</sub>F<sub>8</sub>, C<sub>5</sub>F<sub>8</sub>, C<sub>4</sub>F<sub>6</sub> and C<sub>3</sub>F<sub>6</sub>.

12. (currently amended) The semiconductor device fabricating method of claim 10, 13, wherein the low-k film is one selected from the group consisting of an organic SOG film, an SiOC film and a pure organic film.

13. (original) The A semiconductor device fabricating method of claim 10, fabricating method comprising the steps of:

forming a first interconnection;  
forming a low-k film as an interlayer insulating film on the first interconnection;  
forming a contact hole for electrically connecting the first interconnection and a second interconnection, in the interlayer insulating film comprising the low-k film; and  
forming an interconnection groove for embedding the second interconnection in the interlayer insulating film comprising the low-k film,

wherein, in at least one of the hole forming step and the interconnection groove forming step, plasma etching is conducted under a gas atmosphere including a fluorocarbon gas, O<sub>2</sub> gas and Ar gas, and under the conditions of a pressure of 60 mTorr (7999.32 mPa) or higher and a high-frequency output (RF power) of 600 W or less, and

wherein an etch stop layer is not formed under in the interlayer insulating film comprising the low-k film.

14. (currently amended) The semiconductor device fabricating method of claim 10, 13, wherein a ratio of O<sub>2</sub> to a combined amount of the fluorocarbon gas and O<sub>2</sub> is 20 to 50%.

15. (currently amended) The semiconductor device fabricating method of claim 10, 13, wherein, in both of the hole forming step and the interconnection groove forming step, plasma etching is conducted under a gas atmosphere including a fluorocarbon gas, O<sub>2</sub> gas and Ar gas, and under the conditions of a pressure of 60 mTorr (7999.32 mPa) or higher and a high-frequency output (RF power) of 600 W or less.